



Rely on it.

RENOLIT ALKORPLAN
Metallics Copper



EXCELLENCE
IN ROOFING

Mechanically fastened system

PRODUCT INFORMATION

RENOLIT ALKORPLAN F

Calendered laminated membrane of flexible PVC with woven polyester reinforcing. Conforms to UEAtc guidelines. Available in copper and silver colour. Solvent welding is not allowed.

CE conformity. Certificates are available on our website: www.renolit.com/roofing:

0749-CPD
BC-320-0295-0100-02 (EN 13956)

Product data	Method	Average production values RENOLIT ALKORPLAN F ₃₅₂₇₆ 1.5 mm	Units
Tensile strength	EN 12311-2 (A)	≥1100	N/50 mm
Elongation at break	EN 12311-2 (A)	≥16	%
Dimensional stability (6h at 80 °C)	EN 1107-2	≤0.3	%
Cold crack temperature (-20 °C)	EN 495-5	≤-25	°C
Tear strength	EN 12310-1	≥400 ≥225	N N
Lamination strength	EN 12316-2	≥225	N/50 mm
Vapour diffusion resistance	EN 1931	20,000 (calc. val.)	-
Resistance to static perforation	EN 12730	≥20	kg

Size/Weight	Thickness	Width	Weight	Roll length	Roll weight
RENOLIT ALKORPLAN F ₃₅₂₇₆	1.5 mm	1.05 m	1,95 kg/m ²	20 lm	ca. 41 kg

Standard conditions of sale are included in price lists, all sales of RENOLIT products are made under these conditions. RENOLIT ALKORPLAN is delivered in rolls. Every delivery may contain up to 10% of short rolls (minimum length: 8 m).

Storage

Store dry. Rolls to be parallel and in original packing where possible, do not stack in cross form or under pressure.

