



Rely on it.

RENOLIT ALKORPLUS₈₁₀₀₂
Self-adhesive vapour control layer



EXCELLENCE
IN ROOFING

RENOLIT ALKORPLUS⁸¹⁰⁰²

Self-adhesive vapour control layer

PRODUCT DATA

Properties	Value	Test
Tensile Strength	≥ 190N/50 mm	EN 12311-1
Elongation at Break	≥ 20%	EN 12311-1
Static load resistance	≥ 15 kg ≥ 20 kg	EN 12730 - A EN 12730 - B
Tear resistance	≥ 45 N	EN 12310 -1
Peel resistance of joints	≥ 20N/50mm	EN 12316 -1
Water vapour impermeability	Sd > 1500 m	EN 1931
Impermeability	≥ 60 kPa	EN 1928
Cold crack temperature	-23°C	EN 495
Application Temperature	+5°C/+45°C	

APPLICATION

The application of the vapour control layer must be done according to the system guidelines RENOLIT ALKORPLAN, RENOLIT ALKORTEC or RENOLIT ALKORTOP and in accordance with national and/or regional standards.

PROPERTIES

- Self-adhesive bituminous vapour control layer reinforced with aluminium foil
- Excellent barrier against radon and methane gas
- Excellent resistance to static perforation
- Vapour control layer conform EN 13970
- Fast installation

PACKAGING

Thickness	Width	Length	Weight	Weight/roll
0,8 mm	100 cm	30 lm	0,23 kg/m ²	37kg

STORAGE

The rolls are stored upright.
25 rolls per pallet (750 m²/pallet).

WWW.RENOLIT.COM/ROOFING

RENOLIT Belgium N.V - Export Dpt. - Industriepark De Bruwaan 43 - 9700 Oudenaarde - Belgium T B +32 55 33 98 51 - F +32 55 31 86 58 - renolit.belgium@renolit.com

RENOLIT Cramlington Ltd
Station Road, Cramlington, Northumberland NE23 8AQ - United Kingdom
T +44 1670 718283 - F +44 1670 718367 - renolit.cramlington@renolit.com



Rely on it.