



Rely on it.

RENOLIT ALKORPLUS₈₁₀₆₈

One-component polyurethane glue



EXCELLENCE
IN ROOFING

RENOLIT ALKORPLUS⁸¹⁰⁶⁸

One-component polyurethane glue

For bonding RENOLIT ALKORPLAN A

PRODUCT DATA

• basis:	polyurethane prepolymer	• specific density at 20°C:	1025 kg/m ³
• colour:	yellow, transparent	• solids content (2 hrs, 120°C):	83% (±2%)
• consistency:	liquid	• minimal application temperature:	+5°C
• flash point:	< -7°C	• cleaner:	RENOLIT ALKORPLUS ⁸¹⁰⁴⁴

APPLICATION

- For bonding of RENOLIT ALKORPLAN A.
- On steep slopes where glue may run, it must be spread evenly over the surface. Precautions need also to be taken to avoid the roofing membrane slipping.
- RENOLIT ALKORPLUS adhesives should always be used according to RENOLIT ALKORPLAN A system guidelines. The surface has to be sound, clean and free of standing water. The appropriate quantity of glue (as shown in the installation guidelines) is applied by means of an applicator or by hand and is dispersed evenly over the surface. Glue concentrations are not allowed. After 10 minutes maximum drying time, the membrane is rolled out and pressed firmly into the glue. Total drying time is 1 to 5 hours depending on ambient temperature and humidity.

PROPERTIES

- high bond strength shortly after application
- high temperature stability when installed (- 20°C to + 80°C)
- can be applied with applicator or by hand
- must be spread evenly over the surface
- quick and easy application
- water resistant
- ready to use
- good ageing resistance

PACKAGING

Type	Packaging	Content	Packaging unit
81068	drum	6 kg	84 drums/pallet

Close immediately after use.

STORAGE

Optimum storage temperature between +10 and + 20°C. Frostproof. Max. shelf life: 1 year (for cool storage in original, unopened packaging). Highly flammable. Consult safety indications on packaging and in safety data sheet.

TRANSPORT

UN-N°: 1133

IMDG-CLASS: 3 ; II

RID/ADR/ADNR-CODE: 3 ; II

WWW.ALKORPROOF.COM

RENOLIT Cramlington Ltd
Station Road, Cramlington, Northumberland NE23 8AQ - United Kingdom
T +44 1670 718283 - F +44 1670 590096 - renolit.cramlington@renolit.com



Rely on it.